



厦门科元塑胶有限公司

Xiamen Keyuan Plastic Co.,Ltd.

产品 描 述	增强级PPS
Product Description	Glass Fiber Reinforced PPS Material
产品 等 级	注塑级别
Product Grade	Injection Molding Grade
产品 外 观	本色颗粒
Appearance	Natural Pellet

产品性能参数Data Sheet

项目		典型性能					测试标准
Item							Testing Standard
		KY-S80G30	KY-S80G40	KY-S80G50	KY-S80G60	KY-S80G70	
密 度 Density		1.65 g/10min	1.65 g/10min	1.65 g/10min	1.90 g/10min	1.65 g/10min	ASTM D-792
吸水率 Water Absorption		0.05%	0.05%	0.05%	0.05%	0.05%	ASTM D-570
颜色	Color	Natural	Natural	Natural	Natural	Natural	
熔体流动速率 Melt Flow Rate		23g/10min	25g/10min	26g/10min	28g/10min	30g/10min	ASTM D-1238
拉伸强度 Tensile Strength		23.0 Ksi	22.0 Ksi	21.0 Ksi	20.0 Ksi	19.0 Ksi	ASTM D-638
伸长率 Elongation		1%	1.20%	1.00%	0.90%	0.80%	ASTM D-638
弯曲强度 Flexural Strength		30.0 Msi	29.5 Msi	28.5 Msi	28.0 Msi	27.0 Msi	ASTM D-790
抗拉模数	Tensile Modulus	2.0 Msi	2.1 Msi	2.20 Msi	2.25 Msi	2.3 Msi	ASTM D-790
抗压强度 Compressive Strength		26.5 Ksi	26.0 Ksi	25.8 Ksi	25.5 Ksi	25.0 Ksi	ASTM D-695
弹性模数 Modulus of Elasticity		2.1 Msi	2.2 Msi	2.3 Msi	2.4 Msi	2.5 Msi	ASTM D-638
悬臂梁冲击强度 Izod Impact Strength	1/8 inch	1.8 ft.lbf/in	1.7 ft.lbf/in	1.5 ft.lbf/in	1.4 ft.lbf/in	1.2 ft.lbf/in	ASTM D-256
悬臂梁缺口冲击强度 Izod Notched Impact Strength	1/8 inch	6.5 ft.lbf/in	6.1 ft.lbf/in	5.5 ft.lbf/in	5.0 ft.lbf/in	4.5 ft.lbf/in	ASTM D-256
绝缘破坏电压 Breakdown Voltage		450 V/mil	450 V/mil	450 V/mil	450 V/mil	450 V/mil	ASTM D-149
介电质常数 Dielectric Constant		3.5	3.9	4.3	4.7	5.1	ASTM D-150
介电常数 Permittivity		3.2	3.8	3.89	3.93	4	ASTM D-149
损耗因素 Dissipation Factor		0.0015	0.002	0.028	0.035	0.058	ASTM D-150
损耗因素 Loss Factor		0.00095	0.0014	0.0035	0.0055	0.0088	ASTM D-150
体积电阻率 Volume Resistivity		1×10 ¹⁷ Ω.cm	1×10 ¹⁶ Ω.cm	2×10 ¹⁶ Ω.cm	3×10 ¹⁵ Ω.cm	5×10 ¹⁵ Ω.cm	ASTM D-257
耐电弧	Arc Resistance	110 Sec	125 Sec	135 Sec	150 Sec	167 Sec	ASTM D-495
电弧踪迹	Arc Trail	9.1 in/min	7.1 in/min	5.1 in/min	3.1 in/min	0	UL 746A
CTI踪迹	CTI Trace	0 V	7.1 V	135.1 V	200.1 V	255 V	UL 746A
绝缘电阻 Insulation Resistance		1×10 ¹⁰ Ω	1×10 ¹¹ Ω	1×10 ¹¹ Ω	1×10 ¹² Ω	1×10 ¹² Ω	
UL温度指数 UL Temperature Index		200/220℃	200/220℃	200/220℃	200/220℃	200/220℃	UL
燃烧性 Flammability		V-0/5VA	V-0/5VA	V-0/5VA	V-0/5VA	V-0/5VA	UL 94
热变形温度 Heat Deflection Temperature		>500°F	>500°F	>500°F	>500°F	>500°F	ASTM D-648
使用温度 Use temperature							
加工温度 Processing temperature : 230 - 250 ° C							
模具温度 Mould temperature : 100 - 120 ° C							
背压 Back pressure : ca.10 - 15 bar							
注塑速度 Injection speed : 中/高 medium/high							
干燥 Pre-drying : 需要 necessary							

KEYUAN

注意事项

Matters need attention

除非另有特别说明，产品手册中的所有数据均来源于室温条件（23℃，50%相对湿度）下对标准试样进行的测试。这些数据为实验典型值，真实可靠，仅能作为参考性数据，不能认定为材料性能的最小值。
These technical data in the product brochures are typical data under specific test conditions and not intended for use as limiting specifications.

安全及处理注意事项：

客户可向当地的办事处索要产品的材料安全数据表（MSDS），客户从MSDS 中可得到材料处理、安全和弃置方面的资料，以及当地适用的健康和安全规定的要求。下面所述只是一般注意事项，仅适用于所提供的树脂。用于塑料成型的各类添加剂和加工助剂，以及用于二次加工工序的其它材料有其自身的安全要求，因此必须去了解。

本产品的毒性极低，在正常条件下使用时，人体吸入、眼部及皮肤接触都没有特别问题。不过，在处理、储存、使用或者弃置这些树脂时仍须谨慎小心。工厂场所应保持整洁，以避免粉尘聚积。在加工操作中，应尽量避免接触熔融的树脂。

塑料树脂产品在制造过程中会产生粉尘和气体。对注塑制件进行锯、锉、打磨等操作时产生的粉尘可能会刺激眼睛和上呼吸道。在多尘的生产环境中，建议操作工人使用经有关部门认可的呼吸器或面罩。按正确操作规程要求，塑料加工区应有良好的通风。塑料在加工过程中超过熔融温度时会释放出含有分解物质的烟雾，此类烟雾可能具刺激性。在大多数情况下，一般良好的通风设备便已足够。当有需要时，应使用局部抽气通风方法。

如在工作中会接触到飞扬的微粒而对眼睛造成伤害时，便要配戴防化护目镜。处理本树脂时，若有需要，可戴上隔热手套作保护。

该产品在紫外线作用下会有发黄现象，因此产品存储时应避免太阳光直接照射。

Safety and Handling Notice:

Customers can request NCM Local Offices to provide MSDS of required products. From these MSDS, Customers can gain information on material processing, material safety, and material disposal approaches. At the same time, Customers can know about the local applicable health and safety regulations. The information we provide hereafter is only the general notice, and it is for the provided resin only. The additives and processing agents for plastic molding and other material for secondary processing have their own safety requirements, so Users must learn those safety requirements. This product has quite low toxicity. In normal conditions, it won't cause any serious problem after inhalation, eye or skin contact. But Users still need to be careful when storing, using and disposing these resins. Users shall keep the factory clean and tidy and avoid dust accumulation. Users shall try to prevent themselves from contacting with molten resins during operation.

Plastic resin products would produce dust and gas in their manufacturing process. The dust, caused by sawing, rasping and polishing of plastic injection parts, might irritate eyes and upper respiratory tract. In the dusty production environment, it is suggested that workers wear respirators or masks approved by authoritative department. Plastic processing zone should have good ventilation as the standard operation procedure requests. If the processing temperature exceeds the melting temperature, the plastic would release irritative smoke which contains decomposition materials. In most cases, it is enough to use the general ventilation equipment. If needed, local exhaust ventilation equipment can be used, too.

If working in a place where floating particles might hurt their eyes, Users can wear the chemical safety goggles to protect their eyes. If needed, Users can wear insulated gloves to protect themselves when processing this resin.

This product will turn yellow under UV light, so Users should avoid direct sunlight when storing this product.

KEYUAN